



400, Eastport Blvd.  
Hamilton, Ontario Canada L8H 7S4  
Tél: (905) 549 4561 Fax: (905) 549 0866



## TECHNICAL DATA B.U.R TYPE II

CHARACTERISTICS	UNITS	METHODS	SPECIFICATIONS	
			CSA 123.4-04	Typical Results
Specific Gravity at 25°C (77°F) g/mL		ASTM D70	N/A	1.029
Viscosity by Brookfield at 175°C (347°F)	cP	ASTM D4402	N/A	418
Viscosity by Brookfield at 200°C (392°F)	cP	ASTM D4402	N/A	141
Flash Point, (C.O.C)	°C (°F)	ASTM D92	260 (500) min	295 (563)
Softening Point, Ring and Ball	°C (°F)	ASTM D36	75 - 83 (167-181)	76 (169)
Penetration at 25°C (77°F) 100g, 5s	dmm	ASTM D5	20 - 30	22
Penetration at 45°C (113°F) 50g, 5s	dmm	ASTM D5	80 max.	60
Penetration at 46°C (115°F) 50g, 5s	dmm	ASTM D5	N/A	70
Penetration at 0°C (32°F) 200g, 60s	dmm	ASTM D5	10 min.	11
Ductility at 25°C (77°F) 5cm/min	cm	ASTM D113	N/A	4.5
Volatilization 5h, 163°C (325°F) Weight loss	%	ASTM D6	1.0 max.	0.05
Penetration of Residue at 25°C (77°F) 100g, 5s as % of the original penetration	dmm	ASTM D5	80 min.	85
Solubility in trichloroethylene	%	ASTM D2042	99.0 min.	99.8
<hr/>				
EVT	°C			202 +/- 14
EVT	°F			396 +/- 25

This product meets CSA 123.4-04 specifications.