



400, Eastport Blvd.
Hamilton, Ontario Canada L8H 7S4
Tél: (905) 549 4561 Fax: (905) 549 0866



TECHNICAL DATA B.U.R TYPE III

CHARACTERISTICS	UNITS	METHODS	SPECIFICATIONS	
			CSA 123.4-04	Typical Results
Specific Gravity at 25°C (77°F) g/mL		ASTM D70	N/A	1.03
Viscosity by Brookfield at 175°C (347°F)	cP	ASTM D4402	N/A	1400
Viscosity by Brookfield at 200°C (392°F)	cP	ASTM D4402	N/A	418
Flash Point, (C.O.C)	°C (°F)	ASTM D92	260 (500) min	290 (554)
Softening Point, Ring and Ball	°C (°F)	ASTM D36	90 - 98 (194-208)	92 (199)
Penetration at 25°C (77°F)100g, 5s	dmm	ASTM D5	15 - 25	17
Penetration at 45°C (113°F)50g, 5s	dmm	ASTM D5	55 max.	45
Penetration at 46°C (115°F)50g, 5s	dmm	ASTM D5	N/A	50
Penetration at 0°C (32°F)200g, 60s	dmm	ASTM D5	8 min.	9
Ductility at 25°C (77°F)5cm/min	cm	ASTM D113	N/A	3.5
Volatilization 5h, 163°C (325°F) Weight loss	%	ASTM D6	1.0 max.	0.01
Penetration of Residue at 25°C (77°F) 100g, 5s as % of the original penetration	dmm	ASTM D5	80 min.	85
Solubility in trichloroethylene	%	ASTM D2042	99.0 min.	99.8
<hr/>				
EVT	°C			232 +/- 14
EVT	°F			450 +/- 25

This product meets CSA 123.4-04 specifications.